

# BISATEN SEMILUCIDA

Rev. 11 of 11/09/2018

P. 1 of 2

Technical Data Sheet No. 2309080700

<b>Denomination</b>	<b>BISATEN SEMILUCIDA</b>
<b>Description</b>	Anti-Mold, Sanitizing Water-Based Wall Paint
<b>Main Characteristics</b>	Anti-Mold and Anti-Algae High Resistance to Leaching Washability > 5000 Brush Strokes High Hiding and Masking Power Semi-Gloss
<b>Product Details</b>	Anti-mold, washable, sanitizing water-based wall paint with specific aesthetic and protective features. It offers a very pleasant appearance after drying. Its special film preservatives provide protection from algae and fungus growth on walls. Its use is recommended in all environments where absolute hygiene is required, such as clinics, hospitals, communities, cooperative wine cellars and residential buildings, and offers a guarantee against any fungi and mold attack, especially in humid and poorly ventilated areas <b>Product conforming to VAA Protocol (Food Environment Paints) test report No.21/2000 of Piacenza's Università Cattolica del Sacro Cuore, and HACCP (Hazard Analysis and Critical Control Points) Protocol No.323748 of Istituto Giordano.</b>
<b>VOC Classification (Directive 2004/42/EC)</b>	Matt Paints For Internal Walls & Ceilings EU limit value for this product (cat. A/a): 30 g/l (2010) This product contains max. 30 g/l VOC
<b>Surface Preparation &amp; Application</b>	<b>NEW SUBSTRATES</b> Apply a layer of BISATEN FIXATIVE diluted 1 ÷ 2 with water, after adequate preparation of the substrate. Wait at least 4 hours to recoat. Yield: 14 m <sup>2</sup> /liter. Apply a first layer of BISATEN SEMILUCIDA water-based paint. Wait 6 hours to recoat. Apply a second layer of BISATEN SEMILUCIDA water-based paint.  <b>CONTAMINATED SUBSTRATES</b> Apply ready-to-use BISATEN DETERGENT directly on the surface with a brush; let the solution stand for 24-48 hours in order to have a full neutralization. Remove the inactive mold colonies vigorously with a brush . Apply a layer of BISATEN FIXATIVE diluted 1 ÷ 2 with water. Wait at least 4 hours to recoat. Apply a first layer of BISATEN SEMILUCIDA water-based paint. Wait 6 hours to recoat. Apply a second layer of BISATEN SEMILUCIDA water-based paint.  <b>UNCONTAMINATED PAINTED SUBSTRATES</b> Remove any trace of old poorly anchored or peeling paint. Cover up any surface imperfections with a suitable quick-setting powder filler (STUCK 84) for cracks and deep holes, and with paste filler (SUPERMURALSTUCCO) for superficial defects and/or total fillings. Apply a layer of BISATEN FIXATIVE diluted 1 ÷ 2 with water. Repeat the application of BISATEN SEMILUCIDA water-based paint as above.
<b>Practical Advices</b>	Room Temperature: min. 5°C / max. 35°C Relative Humidity: min. 35% / max. 85% Substrate conditions: Dry
<b>Available Sizes</b>	White..... 13 liters - 5 liters - 2,5 liters
<b>Storage</b>	<ul style="list-style-type: none"><li>Keep container tightly closed in a dry, cool place</li><li>Storage temperature: up to 5°C / below 40°C</li><li>Shelf life: 24 months under optimal temperature and RH (relative humidity) conditions</li></ul>
<b>Safety Standards</b>	<b>Product labeled according to Regulation 1272/2008 (CLP).</b> For further information, reference should be made to the related Material Safety Data Sheet. Empty containers or containers with slight film traces of dried residual product must be disposed of in accordance with local requirements.



# BISATEN SEMILUCIDA

Rev. 11 of 11/09/2018

P. 2 of 2

Technical Data Sheet No. 2309080700

Technical Features	Method	Laboratory Data @ 20°C (68°F), 65% R.H.
Vehicle Type		Vinyl-Versatate
Density (during packaging)	UNI 8910 UNI EN ISO 2811-1	1,270 ÷ 1,320 g/ml
Viscosity Brookfield RVT at 20°C and 20 rpm	ASTM D 2196	8.000 ÷ 12.000 cps
pH after storage	UNI 8311	7,5
% Solids	UNI 8906	By Weight: 55,7 % ± 1 By Volume: 40,8 % ± 1
Dry Film Total Thickness (Contrast Ratio: Hp ≥ 98)	ASTM D 1186 UNI EN ISO 2808	113 µm (microns)
Coverage		3,6 m <sup>2</sup> /liter
Filmability at Low Temperature	UNI 10793	Good at + 5°C
Flash Point	UNI 8909	Non-flammable
Color		White
Dilution (V/V) - Brush		1st Coat..... 50 % - 2nd Coat..... 20%
Dilution (V/V) - Roller		1st Coat..... 40 % - 2nd Coat..... 15%
Thin With		Water
Application Equipment		Roller; Brush
Dry to Touch		1 hour
Dry to Handle		5 - 7 hours
Dry to Recoat		Min. 6 hours – Max. N/A
Applicability: Exteriors / Interiors		Yes / Yes
Tools Cleaning		Water
Dry Film Appearance: Classification Specular Gloss @ 85°	UNI 9389	Semi-Gloss < 60 - ≥ 30 gloss
Resistance To Washing: Classification N. Of Brush Strokes		Excellent ≥ 5000
Water Vapor Permeability	UNI 9396	Classification: Low Water Vapor Diffusion: < 15 g/m <sup>2</sup> . d (= in 24 h )
Dirt Pick-Up	UNI 10792	Δ L --> ≤ 3,0.....Very Low

## Performance Classification according to European Legislation EN 13300

Fineness of Grind	UNI EN ISO 1524	Class.....Fine ≤ 100 µm
Specular Gloss @ 85° Reflectance	UNI EN ISO 2813	Class.....Semi-gloss < 60 and ≥ 10
Washability Wet Scrub Resistance 200 Cycles	UNI EN ISO 11998	Class 1 < 5 µm after 200 cycles

Giuseppe Di Maria S.p.A. Legal Address: Via Enrico Mattei, 4  
90124 PALERMO (PA)

Tel. +39.091.391288 Fax. +39.091.391011  
www.dimaria.it E-mail: dimaria@dimaria.it



Contrast Ratio Hiding Power	UNI EN ISO 6504-3	Class 3 $\geq 95$ and $< 98$
Kubelka-Munk Yield	UNI EN ISO 6504-1	7 m <sup>2</sup> /liter