

ELIOFLEX Fibro

Rev. 02 of 12/11/2018 P. 1 of 3
Technical Data Sheet No. 2411171610

Denomination ELIOFLEX Fibro

Description Elastomeric Acrylic-Siloxane Water-Based Wall Paint Reinforced with Synthetic Fibers

Product Details

Elastomeric filling matte acrylic-siloxane water-based wall paint, reinforced with synthetic fibers, suitable for the protection of thermal insulation systems, crazed surfaces, paints and wall coatings (in general) with or without micro-cracks issues. Excellent filling power; it offers good water vapor permeability. Excellent flexibility even at very low temperatures. It contains cracks up to 200-300 µm wide.

**VOC Classification
(Directive 2004/42/EC)**

One-Pack Performance Coatings.
EU limit value for this product (cat. A/i): 140 g/l (2010)
This product contains max. 120 g/l VOC

**Surface Preparation &
Application**

SUBSTRATES WITH NEW PLASTERS

- After the plaster has been cured, it is always advisable to apply a coat of water-based **Eliofond Acrilico**.
- Allow at least 12 hours to elapse for drying and apply the first coat of **Elioflex Fibro** with a roller.
- Allow another 12 hours to elapse before applying the second coat of **Elioflex Fibro**.
- It is always advisable to apply the product as it is to obtain an adequate thickness (minimum 400 µm of dry paint film), that is sufficient to contain micro-lesions.

SUBSTRATES WITH OLD PAINTS AND VISIBLE LESIONS

- It is always recommended to apply a coat of solvent-based **Eliowall Primer**.
- Allow at least 6 ÷ 8 hours to elapse and start the restoration procedure by applying **Elioflex Fibro** on the cracks with a brush, filling them.
- In the case of cracks up to 1 mm wide, proceed with the application of polyester mesh portions along the lesion dorsal, that will be drowned with a first coat of **Elioflex Fibro** (applied with a roller).
- Allow at least 24 hours to elapse before applying the second coat of **Elioflex Fibro**.
- It is always advisable to apply the product as it is to obtain an adequate thickness (minimum 400 µm of dry paint film), that is sufficient to contain micro-lesions.

Practical Advices

Room Temperature: Min. 5°C / Max. 30°C
Relative Humidity: Min. 35% / Max. 85%
Substrate Conditions: Dry

Available Sizes

20 Kg

Storage

- Keep container tightly closed in a dry, cool place.
- Storage Temperature: up to 5°C / below 35°C.
- Shelf Life: 24 months under optimal temperature and R.H. conditions.

Safety Standards

Product labeled according to **Regulation 1272/2008 (CLP)**.

For further information, reference should be made to the related Material Safety Data Sheet. Empty containers or containers with slight film traces of dried residual product must be disposed of in accordance with local requirements.



ELIOFLEX Fibro

Rev. 02 of 12/11/2018 P. 2 of 3
Technical Data Sheet No. 2411171610

Technical Features	Laboratory Data @ 20°C (68°F), 65% R.H.
Vehicle Type	Acrylic-Siloxane Resins
Specific Weight	1.540 gr/litro
% Solids	By Weight: 68,4 % By Volume: 51,2 %
Color	White Integrated in Eliocolor Performance Tintometric System
Viscosity Brookfield RVT at 20°C and 20 rpm	40.000 ÷ 45.000 cps
Components	One
Dilution (V/V)	Ready-to-Use
Thin With	Water (only for tools cleaning)
Tools	Roller; Brush; Airless Spray Gun
Dry Film Thickness per Coat	205 µm
Coverage at Recommended Film Thickness	2,54 m²/liter – 1,6 m²/kg
Consumption per Coat	625 gr/m²
Dry to Touch	5 ÷ 6 hours
Dry to Handle	24 hours
Dry to Recoat	Min.12 hours
Dry Film Appearance Specular Gloss @ 60°C	Semi-Matte < 30 - ≥ 10 gloss
Resistance to Rural, Light Industrial and Marine Environments	Excellent
Temperature Resistance	From -25°C to +50°C
Rainwater Resistance	The product completes its cross-linking process over a period of 12-15 days under optimal conditions
Elasticity	Good



ELIOFLEX Fibro

Rev. 02 of 12/11/2018 P. 3 of 3
Technical Data Sheet No. 2411171610

Performance Classification according to European legislation EN 1062

Film Appearance	G ₃ Matte 1G.U. 85°
Dry Film Thickness	E ₄ > 200 µm
Grain Size (EN ISO 1524)	S ₂ Medium < 300 µm
Vapor Permeability (UNI EN ISO 7783:2012) "CERTIMAC" Test Report of 03/07/2018	V ₂Medium ≤ 150 - > 15 g/(m ² • d) (= 106 g/m ² d.)
Water Permeability "CERTIMAC" Test Report of 03/02/2018	W ₃ Low.....≤ 0,1 kg/(m ² • h ^{0,5}) (= 0,02 kg/m ² h ^{0,5})
CO ₂ Permeability "CERTIMAC" Test Report of 03/22/2018	C ₁Mean value of the thickness of the equivalent layer of air S _d > 50 m. (S _d = 616,5 m) - <i>The coating is suitable for applications that prescribe "anti-carbonation" products</i>
Cracking Resistance (UNI EN 1062-7) "CERTIMAC" Test Report of 03/29/2018	<i>The Coating is in Class A3, (Crack-bridging): for both tests carried out at +23°C and -10°C</i>
Solar Reflectance and Thermal Emittance (ASTM C 1371-04a) "CERTIMAC" Test Report of 02/26/2018	<i>Average Solar Reflectance, a = 0.84 Thermal Emittance, E = 0.92</i>
Thermal Conductivity (UNI EN 1745; ASTM E 1530, UNI EN 12664) "CERTIMAC" Test Report of 02/28/2018	<i>Average Paint Film Thickness (= 0,71 mm) Thermal Conductivity (= 0,237 ÷ 0,271 W/mk)</i>
Numerical Evaluation of the Contribution to Thermal Transmittance of Masonry Walls Subjected to Vertical Load (UNI EN ISO 6946) "CERTIMAC" Test Report of 03/01/2018	<i>Traditional Walls:</i> ▪ % Variation compared to the standard U-Value (= 0,410) ▪ Thermal Transmittance U-Value (= 1,458 W/m² k) <i>Cutting-Edge Walls:</i> ▪ % Variation compared to the standard U-Value (= 0,075) ▪ Thermal Transmittance U-Value (= 0,251 W/m² k)

THE INFORMATION AND RECOMMENDATIONS CONTAINED HEREIN ARE BASED ON OUR RESEARCH AND ARE BELIEVED TO BE ACCURATE, BUT NO WARRANTY, EXPRESS OR IMPLIED, IS MADE OR SHOULD BE INFERRED. PURCHASERS SHOULD TEST THE PRODUCTS TO DETERMINE ACCEPTABLE QUALITY AND SUITABILITY FOR THEIR OWN INTENDED USE. NOTHING CONTAINED HEREIN SHALL BE CONSTRUED TO IMPLY THE NONEXISTENCE OF ANY RELEVANT PATENTS OR TO CONSTITUTE A PERMISSION, INDUCEMENT OR RECOMMENDATION TO PRACTICE ANY INVENTION COVERED BY ANY PATENT, WITHOUT AUTHORITY FROM THE OWNER OF THE PATENT. FOR FURTHER INFORMATION, DO NOT HESITATE TO CONTACT OUR TECHNICAL TEAM.

