

ELIOTUCCO

Rev. 05 of 07/02/2013 P. 1 of 2
Technical Data Sheet No. 0711932130

| | |
|--|--|
| Denomination | ELIOTUCCO |
| Description | Extra Plaster for Wood and Walls |
| Product Details | Water-based paste-plaster, suitable for filling wooden products and levelling walls. It is easy to sand and has a high filling power; it is recommended only for indoor applications. |
| VOC Classification (Directive 2004/42/EC) | Not intended for uses contained in Legislative Decree No. 161/2006 (in Italy) |
| Surface Preparation & Application | WOODEN SUBSTRATES Apply directly without prior preparation. |
| Practical Advices | Room Temperature: Min. 5°C / Max. 35°C Relative Humidity: Min. 35% / Max. 85% Substrate Conditions: Dry |
| Available Sizes | 2,5 liters - 0,500 liters - 0,250 liters - 20 Kg |
| Storage | <ul style="list-style-type: none">Keep container tightly closed in a dry, cool place.Storage Temperature: up to 5°C / below 35°C.Shelf Life: 18 months under optimal temperature and R.H. conditions. |
| Safety Standards | Product exempt from labelling according to Legislative Decree No. 65/03 (in Italy). For further information, reference should be made to the related Material Safety Data Sheet. Empty containers or containers with slight film traces of dried residual product must be disposed of in accordance with local requirements. |

Giuseppe Di Maria S.p.A. Sede Legale: Via Enrico Mattei, 4
90124 PALERMO (PA)
Tel. +39.091.391288 Fax. +39.091.391011
www.dimaria.it E-mail: dimaria@dimaria.it



ELIOTUCCO

Rev. 05 of 07/02/2013 P. 2 of 2
Technical Data Sheet No. 0711932130

| Technical Features | Laboratory Data @ 20°C, 65% R.H. |
|---|--|
| Vehicle Type | Polyacetovinyl Resins |
| Specific Weight | 1.790 ÷ 1.900 gr/liter |
| % Solids | By Weight: 73,0 % ± 1 By Volume: 48,7 % ± 1 |
| Color | White |
| Product Appearance | Paste-Like |
| Viscosity | Thixotropic |
| Filmability at Low Temperature | Good at + 5°C |
| pH after Storage | 7,5 |
| Components | One |
| Dilution (V/V) | Ready-to-Use |
| Thin With | Water (only for tools cleaning) |
| Tools | Putty Knife |
| Coverage | Variable according to thickness (5 m ² /Kg per coat) |
| Drying Time | 3 ÷ 5 hours |
| Interval for Sanding | 4 ÷ 6 hours |
| Dry Film Appearance Specular Gloss @ 85° | Very Matt < 5 gloss |
| Elasticity | Good |
| Sandability | Excellent |
| Adherence | Excellent |
| Temperature Resistance | + 60°C |

THE INFORMATION AND RECOMMENDATIONS CONTAINED HEREIN ARE BASED ON OUR RESEARCH AND ARE BELIEVED TO BE ACCURATE, BUT NO WARRANTY, EXPRESS OR IMPLIED, IS MADE OR SHOULD BE INFERRED. PURCHASERS SHOULD TEST THE PRODUCTS TO DETERMINE ACCEPTABLE QUALITY AND SUITABILITY FOR THEIR OWN INTENDED USE. NOTHING CONTAINED HEREIN SHALL BE CONSTRUED TO IMPLY THE NONEXISTENCE OF ANY RELEVANT PATENTS OR TO CONSTITUTE A PERMISSION, INDUCEMENT OR RECOMMENDATION TO PRACTICE ANY INVENTION COVERED BY ANY PATENT, WITHOUT AUTHORITY FROM THE OWNER OF THE PATENT. FOR FURTHER INFORMATION, DO NOT HESITATE TO CONTACT OUR TECHNICAL TEAM.

Giuseppe Di Maria S.p.A. Sede Legale: Via Enrico Mattei, 4
90124 PALERMO (PA)
Tel. +39.091.391288 Fax. +39.091.391011
www.dimaria.it E-mail: dimaria@dimaria.it

